Jerrican - 2 1/2 Gallon, Blue



C Enlarge

Store or transport chemicals and non-hazardous liquids.

Availability: In Stock

Unit Weight: 1.60 lbs.

Catalog Page 523

Country of Origin: USA

Instructions

Test Report

- · High-density polyethylene.
- FDA compliant.
- Caps included.

■ Additional Info ⊕ Parts/Accessories ⊕ Email Page ⊕ Add to Favorites Request a Catalog

DIMENSIONS:

- Actual: 9.3 x 8.3 x 11.5" (L x W x H)
- Opening: 2"

TEMPERATURE:

• Filling Container-Maximum: 180 F

COMPATIBILITY:

- Can be used with H-2955- Drum Faucet.
 - o Drill a hole in center of cap and screw the faucet into the cap.

COMPATIBLE SHRINK BANDS:

- 1" Clear, Perf: S-12234
- 1" Clear, Non-Perf: S-12225
- 2" Clear, Perf: S-18629
 Safety: S-16289

CAPACITY:

Overflow: 2.8 gal

WEIGHT:

676 grams

FEATURES:

- Cap:
 - o Size: 63 mm

 - Works with 3/4" NPT faucet or spigot.
 Leakproof when tightened to 150 in/lb.

RECYCLING:

Recyclable

• While made of FDA compliant resins, it is recommended to clean before first use.

SPECIFICATIONS:

BPA Free



Design Qualification Test Report # 2004-22 done by
Priority Plastics, Inc.
Test Report 2017-01
January 13, 2017
Page 3 of 22

SECTION I: Certification

Periodic Retest 2.5 Gallon Rectangle HDPE Packaging (Equistar LP5100 Resin)

Priority Plastics, Inc. certifies that the packaging referenced above has passed the standards of the DEPARTMENT OF TRANSPORTATION'S TITLE 49 CFR; Performance Oriented Packaging Standards, Section 178. It is the responsibility of the end user to determine authorization for use under these regulations. The use of other packaging methods or components other than those documented in this report may render this certification invalid.

	S	SUMMARY OF I	PERFORMANCE TES	TS	- 11
UN/DOT TEST	CFR REFERENCE	TEST LEVEL	TEST CONTENTS	TEST COMPLETED	TEST RESULTS
Drop	178.603	1.6 m	Windshield Fluid/Antifreeze Coolant 50/50 Diluted (WW?A)	January 6, 2017	PASS
Leakproofness	178.604	20 kPa – 5 Min. 3 PSI	Empty	January 5, 2017	PASS
Hydrostatic	178.605	150 kPa - 30 Min.	Water	January 5, 2017	PASS
Dynamic Compression- Stacking	178.606	532,5 lbs	Water	January 5, 2017	PASS
Vibration	178.608	1.6mm - 1 Hr	Water	January 5, 2017	PASS
UN MARKING (CFR 49 – 178	.503)		n	M5105	
PACKAGING IDENTIFICATION CODE:			3H1 (178.509)		
PERFORMANCE STANDARD:			Y (Packaging meets Packing Group II test)		
MAXIMUM PRODUCT SPECIFIC GRAVITY:			1.6		
INTERNAL TEST PRESSURE:			150 kPa		
YEAR OF MANUFACTURE:			**Insert year the packaging is manufactured		
STATE AUTHORIZING THE MARK:			USA		
PACKAGING CERTIFICATION AGENCY:			(M5105) Priority Plastics, Inc.		
PACKAGE IDENTIFICATION:			M5105		
PERIODIC RETEST DATE:			January 6, 2018		

In the event of future changes to the above referenced test standard, it is the responsibility of Priority Plastics to determine whether additional testing or updating of past testing is necessary to verify that the packaging tested remains in compliance with those standards.

MANUFACTURER:

Priority Plastics, Inc. 500 Industrial Park Road Portland, IN 47371 Donna Noll Quality Manager Priority Plastics, Inc. 500 Industrial Park Rd Portland, IN 47371



Design Qualification Test Report # 2004-22 done by
Priority Plastics, Inc.
Test Report 2017-01
January 13, 2017
Page 4of 22

SECTION II & V: PACKAGING DESCRIPTIO	N / COMPONENT DRAWINGS
2.5 Gallon Rectangle No Vent HDPE Packs	aging (Equistar LP5100 Resin)
	Certification Type: Periodic Retest Packaging Code Designation: 3H1 Packing Group; II Specific Gravity: 1.6 Hydrostatic Pressure: 150 kPa TEST SAMPLE PREPARATION (Refer to Section_IV) Overall Package Tare Weight:718.35Grams (1.6 Lbs.) Fill Capacity (98% Overflow): WW/A 10689 Grams Water 10324 Grams Package Test Weight: WW/A: 11.407 Kg (25.15 Lbs.) Water 11.402 Kg (25.14 Lbs.) Calculated Package Gross Mass17.2 Kg (37.9 Lbs.) CLOSING METHODS Application Torque for 63mm Cap: 150 In-Lbs. Equipment for 70mm Cap: Torque Wrench # GP-050 H & V-GP-163 A